



Adolf Würth GmbH und Co. KG  
 Reinhold-Würth Str. 12 - 17  
 74653 Künzelsau  
 Germany

Eurofins Product Testing A/S  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 voc@eurofins.dk  
 www.eurofins.com/voc-testing

Date  
 16 March 2017  
 Our ref.  
 392-2015-00357601\_07

## Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### Sample material

Sample identification	WIT-UH 300 – Batch no. 67405615 (25.02.2015)
Product type	Multipurpose construction adhesive
Product data, according to manufacturer	Density: 1.765 g/ml at 20 °C ** Water content: 5.56 g/l** Exempt compounds: none ***
Date received	09 November 2015
Analytical period	09 November 2015 – 23 November 2015

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U <sub>m</sub> (%)
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:  
 ( [g all volatiles] - [g water] - [g exempt compounds] ) / ( [l material] - [l water] - [l exempt compounds] )

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

### Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
	98.1	0.3**	0***	28	70*

\* VOC limit for “Multipurpose Construction Adhesive”

\*\* Given by the client

\*\*\* No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Morten Sielemann  
 Analytical Chemist